








<b>Technisches Datenblatt / Fiche Technique / Technical data sheet</b>			
Article No. FP30010150FR		Issued : duarcr 18/07/2022	
Name of the fabric: Beja FR		Revised: 0	
Group of article	Scenic		
Application	Curtains and Upholstery  		
Type of weave	Velvet		
Content of pile %	100% CO		
General composition	100% CO		
Weight g/m <sup>2</sup>	450g/m <sup>2</sup> ± 5%		
Overall Width cm	154 cm ±2cm		
Cutable Width cm	150 cm ±2cm		
Test	Testing method	Test Standard	
Abrasion Martindale	Determination of the abrasion resistance 12KPa	ISO 12947-2 -3	≤10% 40.000 rubs
Tensile Strength	Tensile properties of fabrics (N)	ISO 13934 – 1	Warp ≥ 200 N Weft ≥ 400N
Elongation	Tensile properties of fabrics (%)	ISO 13934 – 1	Warp ≥ 6% Weft ≥ 8%
Seam slippage	Slippage Resistance of Yarns at a Seam (180N)	EN ISO 13936-2	Warp ≤ 4mm Weft ≤ 4mm
Colour fastness to Rubbing	Specifies a method for determining the resistance of the colour of textiles	ISO 105-X12	Light colours Dry – 3/4 Dark colours Dry – 3
Colour fastness to Dry Cleaning	Tests for colour fastness	ISO 105-D01	Color Change – 4 Color Staining – 3
Colour fastness to Artificial Light	Specifies a method intended for determining the effect on the colour of textiles	ISO 105-B02	Light = 3 Dark= 4
Flammability	Fire Resistance	NF P-92-503/507	M1
Recommended Care instruction	No Wash; No Iron Only Dry Clean With Perchloroethylene     		

**This velvet has been piece-dyed, following a certain mechanical working process. Batch to batch chromatic variations must be considered as normal and are to be evaluated with the usual tolerance of this type of fabric. Work separately dye lots.**